

Preliminary Product Information

THERMFLOW™ T454 and T506 Phase Change Thermal Interface Material

DESCRIPTION

THERMFLOW™ T454 and T506 thermal interface pads are phase change materials specially formulated for use in high performance devices requiring minimum thermal resistance for maximum heat sink performance and component reliability. These pads consist of an electrically non-conductive, dry film that softens at device operating temperatures resulting in “grease-like” performance. THERMFLOW T454 and T506 are unsupported free films that can yield very thin bond lines between a hot component and a heat sink or heat plate. T454 is 0.005 inches thick, while T506 is 0.010 inches thick which is beneficial for larger surface areas with greater flatness tolerances. These materials are designed to perform best under clip/fastener pressures of 5 - 60 PSI; other THERMFLOW products are available which may have superior performance under different application pressures.

APPLICATION

THERMFLOW T454 and T506 pads are applied by preheating the surface of the heat sink to 55-65°C. Remove the THERMFLOW pad from the clear release liner and carefully position the pad on the warm heat sink. Once the heat sink has cooled, it can be packaged and shipped normally. Prior to assembly of the heat sink onto the heat-dissipating component, it is recommended that the blue protective liner be removed from the pad only at temperatures below 30°C. For best blue liner removal results, the pad should be in place on the heat sink for a minimum of 30 minutes at a temperature below 30°C before liner removal. Dents and minor scratches in the material will not affect performance since the material is designed to flow at typical microprocessor operating temperatures. THERMFLOW pads can be removed for rework using a single-edged razor and then cleaning the surface with isopropanol (IPA) solvent.

	Typical Properties	T454	T506	Test Method
CONSTRUCTION	Carrier	None	None	---
	Color	White to slightly gray	White to slightly gray	Visual
	Thickness, inch (mm)	0.005 (0.13)	0.010 (0.25)	ASTM D374
THERMAL	Thermal Impedance, °C-in ² /W @ 50°C, 50 psi	0.025	0.025	ASTM D5470 modified
	Phase Change Temperature, °C	43	43	ASTM D3418
	Operating Temperature Range, °C	-60 to +125	-60 to +125	---
MECH	Specific Gravity	1.1	1.1	ASTM D792

TB454_506
December 2001

Preliminary Product Information

www.chomerics.com

North America • 77 Dragon Court, Woburn, MA 01888-4014 TEL +(1) 781-935-4850 FAX +(1) 781-933-4318
Europe • Marlow, Bucks, UK TEL +(44) 1628 404000 FAX +(44) 1628 404090
Asia Pacific • Hong Kong TEL +(852) 2 428 8008 FAX +(852) 2 423 8253
South America • São Paulo, Brazil TEL +(55) 11 3917 1099 FAX +(55) 11 3917 0817

CHOMERICS 

 **Parker** Seals

NOTICE: The information contained herein is to the best of our knowledge true and accurate. However, since the varied conditions of potential use are beyond our control, all recommendations or suggestions are presented without guarantee or responsibility on our part and users should make their own tests to determine the suitability of our products in any specific situation. **This product is sold without warranty either expressed or implied, of fitness for a particular purpose or otherwise, except that this product shall be of standard quality, and except to the extent otherwise stated on Chomerics' invoice, quotation, or order acknowledgement.** We disclaim any and all liability incurred in connection with the use of information contained herein, or otherwise. All risks of such are assumed by the user. Furthermore, nothing contained herein shall be construed as a recommendation to use any process or to manufacture or to use any product in conflict with existing or future patents covering any product or material or its use.