



MATERIAL REPORT

DATE: 03/22/00

TITLE: Evaluation of Parker's Compound NA192-50

CONCLUSION: Compound NA192-50 meets or exceeds all requirements of subject specification.

Recommended Temperature Range: -55 to 225F

Recommended for: petroleum oils, water (up to 212F),
Salt & Alkali solutions, weak acids

Not Recommended for: aromatic fuels, strong acids,
glycols, ozone, polar solvents

Parker O-Ring Division
2360 Palumbo Drive
Lexington, Kentucky 40512
(859) 269-2351

REPORT DATA

<u>Original Physical Properties, ASTM D1414, D2240</u>	<u>NA192-50 Test Results</u>
Hardness, Shore A, pts.	51
Tensile Strength, psi	1651
Ultimate Elongation, %	633
Compression Set, ASTM D395 Method B (22 hrs. @ 212°F)	
Percent of Original Deflection (½" buttons)	9
Dry Heat Resistance, ASTM D573 (70 hrs. @ 212°F)	
Hardness Change, pts.	+12
Tensile Change, %	-16
Elongation Change, %	-30
Fluid Immersion, ASTM D471 ASTM #1 Oil, (70 hrs. @ 212°F)	
Hardness Change, pts.	+8
Tensile Change, %	-3
Elongation Change, %	-21
Volume Change, %	-6
Fluid Immersion, ASTM D471 IRM 903 Oil, (70 hrs. @ 212°F)	
Hardness Change, pts.	-5
Tensile Change, %	-20
Elongation Change, %	-17
Volume Change, %	+10
Low Temperature Brittleness, ASTM D2137	
Nonbrittle after 3 min. @ -31°F	Passed