



MATERIAL REPORT

DATE: 03/18/02

TITLE: Evaluation of Parker's Compound NM156-75

CONCLUSION: Compound NM156-75 meets or exceeds all requirements of subject specification.

Recommended Temperature Range: -65 to 250F

Recommended for: petroleum oils, water (up to 180F),
Salt & Alkali solutions, weak acids

Not Recommended for: aromatic fuels, strong acids,
glycols, ozone, polar solvents

Parker O-Ring Division
2360 Palumbo Drive
Lexington, Kentucky 40512
(859) 269-2351

REPORT DATA

<u>Original Physical Properties, ASTM D1414, D2240</u>	<u>NM156-75</u> <u>Test Results</u>
Hardness, Shore A, pts.	75
Tensile Strength, psi	1661
Ultimate Elongation, %	167
Modulus @ 100%, psi	900
Specific Gravity	1.28
Fluid Immersion, ASTM D471 Mil-H-5606, (70 hrs. @ 275°F)	
Hardness Change, pts.	-7
Tensile Change, %	-38
Elongation Change, %	-22
Volume Change, %	+14
Compression Set, ASTM D395 Method B Mil-H-5606, (70 hrs. @ 275°F)	
Percent of Original Deflection (plied)	40
Fluid Immersion, ASTM D471 Mil-H-83282, (70 hrs. @ 275°F)	
Hardness Change, pts.	-6
Tensile Change, %	-31
Elongation Change, %	-32
Volume Change, %	+7
Compression Set, ASTM D395 Method B Mil-H-83282, (70 hrs. @ 275°F)	
Percent of Original Deflection (plied)	43
Low Temperature, ASTM D1329 TR-10, °F	-55