

Test data provided by raw material manufacturer or an ISO 17025 registered 3rd party lab. Original test data is stored in the Darcoïd Compound Database



1/12/2023

Darcoïd Compound: 5053

COMPOUND DATA SHEET

VMQ, 40 Shore A

ORIGINAL PROPERTIES	TEST METHOD	RESULT
Hardness, Shore A, pts	ASTM D-2240	42
Tensile Strength, psi	ASTM D-412	1305
Elongation, %	ASTM D-412	650
Tear Resistance, Die B, ppi	ASTM D-624	120
Compression Set, 22 Hrs @ 150°C, %	ASTM D-395	25

950 3rd Street | Oakland, California 94607 | (800) 632-7264

This document is the confidential property of Darcoïd and is not to be shared with any companies or persons outside of the nondisclosure agreement without the written permission from Darcoïd.

