



## MATERIAL REPORT

REPORT NUMBER: KJ0667-70

DATE: 01/09/89

- TITLE:** Evaluation of Parker Compound E0667-70 meets ASTM D2000 5CA 715 A25 B35 C32 F18 G21 EA14
- PURPOSE:** To verify Parker Compound E0667-70 meets all phases of the specification.
- CONCLUSION:** Parker Compound E0667-70 meets all phases of the specification.

Recommended temperature limits: -70°F to 250 °F

Recommended For

Hot water and steam

Glycol based brake fluid

Many organic and inorganic acids

Cleaning agents, soda and potassium alkalis

Phosphate –ester based hydraulic fluids

Silicone oil and grease

Polar solvents

Ozone, Aging and weather resistance

Not Recommended For

Mineral oil products



## REPORT DATA

Report Number: KJ0667-70

5CA 715 A25 B35 C32 F18 G21 EA14

<u>ORIGINAL PHYSICALS</u>	<u>SPEC</u>	<u>E0667-70</u>
Hardness, Shore A, pts.	65-75	70
Tensile Strength, min..	1500	1993
Elongation, min.	200	255
<u>HEAT AGE (A25)</u>		
<u>70 HRS. @ 257°F</u>		
Hardness Change, max.	+10	+1
Tensile Change	-20	+16.7
Elongation Change	-40	+7.8
<u>HEAT AGE (BASIC)</u>		
<u>70 HRS. @ 257°</u>		
Hardness Change	±15	+1
Tensile Change	±30	+16.7
Elongation Change, max.	-50	+ 7.8
<u>COMPRESSION SET, (BASIC)</u>		
<u>22 HRS. @ 212°F</u>		
% of original deflection	60% max.	9.9%
<u>COMPRESSION SET (B35)</u>		
<u>22 HRS. @ 257°F</u>		
% of original deflection	50% max.	15.8%
<u>RESISTANCE TO OZONE (C32)</u>		
<u>METHOD D1171</u>		
<u>EXPOSURE METHOD B</u>	Pass	specimen not suitable for testing
<u>(F18)</u>		
<u>Low Temp, Brittleness</u>		
<u>D2137, Method A</u>		
nonbrittle after		
3' @ -50°C (-58°F)	Pass	Passed
<u>(G21)</u>		
<u>Tear Resistance</u>		
<u>Method D624, Die C</u>		
Min. KN/M	26 min.	38.4
<u>(EA14)</u>		
<u>Water Resistance</u>		
<u>70 HRS. @ 212°F</u>		
Volume Change, %	± 5	+3



**Compound Data Sheet**  
**Parker O-Ring Division United States**

---

Parker O-Ring Division  
2360 Palumbo Drive  
Lexington, Kentucky 40509  
(859) 269-2351