



MATERIAL REPORT

DATE: 12/26/2002

TITLE: Evaluation of Parker Compound E1267-80 to aerospace specification NAS1613 Rev. 4.

PURPOSE: To determine if Parker Compound E1267-80 meets all phases of the above specification

CONCLUSION: E1267-80 meets or exceeds all phases of the above specification.

Recommended temperature limits: -70°F to 250 °F

Recommended For

Hot water and steam

Glycol based brake fluid

Many organic and inorganic acids

Cleaning agents, soda and potassium alkalis

Phosphate –ester based hydraulic fluids

Silicone oil and grease

Polar solvents

Ozone, Aging and weather resistance

Not Recommended For

Mineral oil products



Compound Data Sheet
Parker O-Ring Division United States

REPORT DATA

Testing per NAS-1613 (Rev. 4)

TEST DESCRIPTION	REQUIREMENT	E1267-80 Class 1	Class 2 Type 4, High Density	Class 1
SPECIFIC GRAVITY	observed value	Type 4, Low Density Chevron HyJet IV-A + 1.19	Skydrol 500 B-4 1.19	Type, Low Density Skydrol LD-5 1.19
DUROMETER HARDNESS (SHORE A)				
-NO SOAK (as furnished)	observed value	80	80	80
-22 hours at 250 deg in Fluid	-10 pts	-7	-4	-9
-70 hours at 160 deg in Fluid	- 5 pts	-3	-2	-5
-70 hours at 250 deg in Fluid	-12 pts	-8	-5	-8
-670 hours at 225 deg in Fluid	-15 pts	-7	-5	-7
VOLUME SWELL (%)				
*.040-.103 size				
-22 hours at 250 deg in Fluid	0-15 %	11.1	7.5	11.7
-70 hours at 160 deg in Fluid	0-10 %	6.2	4.4	5.2
*116-.275 size				
-22 hours at 250 deg in Fluid	0-15 %	12.1	8.1	12.1
-70 hours at 160 deg in Fluid	0-08 %	7.2	4.3	2.7
-70 hours at 250 deg in Fluid	0-15 %	11.7	8.1	11.6
-334 hours at 225 deg in Fluid	0-17 %	12.8	8.7	10.7
-670 hours at 225 deg in Fluid	0-17 %	13.1	8.7	9.8
TENSILE AND ELONGATION (psi-%)				
-NO SOAK (as furnished)	1400 psi at 125%	1734 at 162	1734 at 162	1734 at 162
-22 hours at 250 deg in Fluid	1350 psi at 125%	1498 at 148	1580 at 150	1768 at 180
-70 hours at 250 deg in Fluid	1300 psi at 125%	1480 at 145	1600 at 148	1571 at 171
-334 hours at 225 deg in Fluid	1200 psi at 125%	1460 at 132	1500 at 153	1583 at 171
COLD TEMPERATURE RETRACTION (deg F)				
-TR-10	-50	-53.5	-53.5	-53.5
-TR-70	-18	-22.5	-22.5	-22.5
COMPRESSION SET (%)				
-NO SOAK, 22 hours at 250 deg in air	30%	8.4	8.4	8.4
-22 hours at 250 deg in Fluid	20%	2.5	3.8	1.1
-70 hours at 160 deg in Fluid	20%	1.4	3.1	6.6
HIGH TEMPERATURE AIR AGING (Shore A)				

Parker O-Ring Division
2360 Palumbo Drive
Lexington, Kentucky 40509
(859) 269-2351



Compound Data Sheet

Parker O-Ring Division United States

-70 hours at 300 deg				
-Durometer hardness (Shore A)	+10	+4	+4	+4
-Tensile & elongation (psi/%)	-25/-10	-8/-4	-8/-4	-8/-4
MODULUS (psi)	800	885	885	885
CORROSION AND ADHESION	PASS/FAIL	Pass	Pass	Pass