



**Compound Data Sheet**  
**O-Ring Division United States**

---

# MATERIAL REPORT

REPORT NUMBER: KB4491

DATE: 03/01/85

**TITLE:** Evaluation of Parker Compound N0750-80

**PURPOSE:** To document conformance to acceptance tests.

**CONCLUSION:** Parker compound N0750-80 meets these requirements

**Recommended Temperature Range:** -25 to 250F

**Recommended for:** petroleum oils, water (up to 212F),  
Salt & Alkali solutions, weak acids

**Not Recommended for:** aromatic fuels, strong acids,  
glycols, ozone, polar solvents

Parker O-Ring Division  
2360 Palumbo Drive  
Lexington, Kentucky 40512  
(859) 269-2351

# REPORT DATA

Report Number: KB4491

<u>ORIGINAL PHYSICAL PROPERTIES</u>	<u>SPECIFICATION</u>	<u>COMPOUND:N0750-80</u> <u>SIZE: 2-220 O-RINGS</u>
Hardness, Shore A, pts.	75 - 85	85
Tensile Strength, psi.	1800 min.	3053
Elongation, %	150 min.	232
Permanent set @ 100%	5%	3%
Low temp. flex., 5 hrs @ -40°F	No cracks	No cracks
 <u>ASTM #3, 70 HRS @ 212°F</u>		
Hardness, Shore 'A'	± 10	85 (0)
Volume Change, %	+5 to +30	+11.0
Low temp. flex., 5 hrs. @ -40°F	No cracks	No cracks
180° Flat Bend	No cracks	No cracks
 <u>ASTM #1, 70 HRS @ 300°F</u>		
Hardness, Shore 'A'	± 10	88 (+3)
Tensile, psi	-30% max.	2393 (-21.6)
Elongation, %	-80% max.	129 (-44.4)
Volume Change, %	-5 to +30%	-0.8
Low temp. flex., 5 hrs. @ -40°F	No cracks	No cracks
180° Flat Bend	No cracks	No cracks
 <u>MIL-0-5606C, 70 HRS @ 250°F</u>		
Hardness, Shore 'A'	± 10	83 (-2)
Tensile, psi	-50	3465 (+13.5)
Elongation, %	-80	335 (+44.3)
Volume Change, %	0 to +30	+11.3
Low temp. flex., 5 hrs @ -40°F	No cracks	No cracks
180° Flat Bend	No cracks	No cracks
 <u>AIR OVEN AGE, 70 HRS @ 212°F</u>		
Hardness, Shore 'A'	± 10	88 (+3)
Tensile, psi	-30% max.	4207 (+37.8)
Elongation, %	-80% max.	189 (-18.5)
Low temp. flex., 5 hrs @ -40°F	No cracks	No cracks
180° Flat Bend	No cracks	No cracks
 <u>COMPRESSION SET, 25%,</u> <u>70 HRS @ 212°F</u>		
% of original Deflection	50% max.	28.6