



Compound Data Sheet
O-Ring Division United States

MATERIAL REPORT

REPORT NUMBER: KK0964
DATE: 3/29/94

TITLE: General evaluation of Parker Compound N0757-70.

PURPOSE: To obtain general test data.

CONCLUSION: In January 1994, Parker Compound N0757-70 was approved by NSF for NSF Standard 61.

Recommended Temperature Range: -30 to 225F

Recommended for: petroleum oils, water (up to 212F),
Salt & Alkali solutions, weak acids

Not Recommended for: aromatic fuels, strong acids,
glycols, ozone, polar solvents

Parker O-Ring Division
2360 Palumbo Drive
Lexington, Kentucky 40512
(859) 269-2351

REPORT DATA

Report Number: KK0964

ORIGINAL PHYSICAL PROPERTIES

Hardness, Shore A, pts.

Tensile Strength, psi.

Elongation, %

Modulus @ 100%

Specific Gravity

N0757-70

2-214 O-rings

70

2904

270

733

1.25

COMPRESSION SET

70 HRS. @ 212° F

% of Original Deflection

25.7

COMPRESSION SET

70 HRS. @ 257° F

% of Original Deflection

31.4