



MATERIAL REPORT

REPORT NUMBER: KK2214
DATE: 2/20/98

TITLE: General evaluation of N1219-60.

PURPOSE: To provide general information.

CONCLUSION: N1219-60 is a NSF51 approved material exhibiting typical physical properties.

Recommended Temperature Range: -30 to 225F

Recommended for: petroleum oils, water (up to 212F),
Salt & Alkali solutions, weak acids

Not Recommended for: aromatic fuels, strong acids,
glycols, ozone, polar solvents

Parker O-Ring Division
2360 Palumbo Drive
Lexington, Kentucky 40512
(859) 269-2351

REPORT DATA

Report Number: KK2214

NSF STANDARD 51 COMPOUND

<u>N1219-60</u>	<u>Production Limits</u>	<u>Typical Data</u>
Hardness	60 ± 5	62
Tensile	1800 min	2100
Elongation	400 min	525
Specific Gravity	1.26 (±.02)	1.26